# ASTRO SHIELD WHITE

REFLECTIVE INSULATION

White-Faced Reflective Insulation


## ASTROSHIELD WHITE I

White bubble - MPET

## ASTROSHIELD WHITE II

White Bubble / White Bubble / MPET





- Reduces Building Condensation
- Install With White or Reflective Face Exposed to the Interior
- Forms An Effective Vapor Barrier
- Reduces Heat Loss in Winter, Heat Gain in Summer
- Not Effected By Moisture and Humidity
- No Special Handling or Breathing Protection Required
- Bird, Rodent and Insect Resistant
- Not Appropriate for Open Sided Buildings

### ANOTHER GOOD IDEA FROM



INNOVATIVE ENERGY, INC

Reflective Insulation Radiant Barriers Insulated Packaging

800-776-3645

www.insul.net • info@insul.net

#### PERFORMANCE SPECIFICATIONS

#### For use in:

Agricultural and commercial buildings including metal structures.

#### For use as:

- 1. A condensation barrier in heated or unheated commercial buildings used for warehousing, poultry and animal confinement.
- 2. A radiant barrier in unheated commercial buildings used for warehouse and animal confinement.
- 3. As a "white" facing for ceiling applications in commercial buildings...and excellent alternative to white vinyl-faced fiberglass batts.

#### Construction:

95% Replective MPET CICM.

Polyethylene White Bubble, 3/16 inch (ASTRO-WHITE 1), 5/16 inch (ASTRO-WHITE 2)

#### **Properties:**

Total Weight: Nominal ASTRO-WHITE I: 34LBS MSF

ASTRO-WHITE II: 60LBS MSF

Flame Spread Index: ASTM E-84 ASTRO-WHITE I: 0

ASTRO-WHITE II: 0

Smoke Index: ASTM E-84 ASTRO-WHITE I: 20

ASTRO-WHITE II: 25

Class A Class 1

Puncture Resistance: ASTM F-1306 ASTRO-WHITE I: 78 PSI

ASTRO-WHITE II: 238 PSI

Emissivity: ASTM E-408 5% Reflectivity: ASTM E-408 95%

R-Value: ASTM C-236 ASTRO-WHITE I: Downward 5.5

ASTRO-WHITE II: Downward 6 ASTRO-WHITE I: Horizontal 4.5 ASTRO-WHITE II: Horizontal 5

Water Vapor Transmission: ASTM E-96 .008

Melting Point 250°F

Operating Temperature Range -60°F to 180°F



INNOVATIVE ENERGY, INC Reflective **Insulation** Radiant **Barriers** Insulated **Packaging** 

800-776-3645